



Optileb V Range

Physiologically safe, fully synthetic compressor oils

Description

Castrol Optileb™ V are fully synthetic compressor oils based on polyalphaolefin basestocks of ISO viscosity grades 46, 68 and 100 for the lubrication of compressors in the food and beverage and pharmaceutical industries. They are formulated only with raw materials which are in conformity with NSF H1 requirements for incidental contact with foodstuffs.

Application

- Screw-type, reciprocating and sliding vane air compressors

Conditions of Use

- Please observe the viscosity guidelines specified by the manufacturer.
- CASTROL OPTILEB V series are compatible with conventional plastics and sealing materials which resistant to low-viscous mineral oils.
- During changeover from a standard mineral oil-based product to CASTROL OPTILEB V series please flush the system thoroughly and monitor the condition of filters.

Advantages

- NSF H1 approved
- Halal and Kosher approved.
- Odorless, tasteless and colorless
- Compatible with sealing materials resistant to mineral oils
- High viscosity index, low viscosity-temperature dependence
- High oxidation stability
- Minimum residue formation
- Excellent water separation ability
- Good wear protection
- Compatible with mineral oil
- Extended service life in comparison with mineral oil

Typical Characteristics

Name	Method	Units	V 46	V 68	V 100
Colour	ASTM D1500	-	Colourless	Colourless	Colourless
Base Oil	-	-	PAO	PAO	PAO
ISO Viscosity Grade	-	-	46	68	100
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	834	837	845
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	46.81	66.23	95.45
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	7.8	10.26	13.62
Viscosity Index	ISO 2909 / ASTM D2270	-	136	141	144
Pour Point	ISO 3016 / ASTM D97	°C/°F	-48/-54	-45/-49	-45/-49
Flash Point - open cup method	ASTM D2592 / ASTM D92	°C/°F	242/468	242/468	242/468
Carbon residue - Conradson test - after air ageing	DIN 51352-2	%wt	0.13	0.13	0.13
Water Separation @ 54°C / 129°F (40/37/3)	ISO 6614 / ASTM D1401	min	6.5	11	-
Water Separation @ 82°C / 180°F (40/37/3)	ISO 6614 / ASTM D1401	min	-	-	3.5

Subject to usual manufacturing tolerances.

Optileb V Range

26 Feb 2013

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

www.castrol.com/industrial