



## Product Data

# Castrol Optitemp® HT 2 & HT 2 EP

High Temperature Greases for Long-term Lubrication

### Description

**Castrol Optitemp® HT 2 & HT 2 EP** are high performance greases for long-term lubrication of rolling and sliding bearings at high operating temperatures as well as at normal or medium bearing pressures. **Castrol Optitemp® HT 2** light-colored, while **Castrol Optitemp® HT 2 EP** has a dark color due to the molybdenum disulphide contained in it. It features an even higher load bearing capacity and good emergency running properties.

### Applications

- For thermally loaded rolling and sliding bearings such as fan bearings in the textile, wood, plastics and food industries as well as in stove furnaces of the automotive industry
- For steam-heated calender or drying cylinder bearings
- As sealing grease for labyrinth seals at high temperatures
- For the application in slightly acidic or alkaline atmospheres
- **Castrol Optitemp® HT 2 EP** is especially suited for friction points subjected to increased loads or when special emergency running properties are required
- Both greases are USDA-H2 authorized and suited for the use in the food and beverage industries.

### Advantages

- Optitec® - Optimol technology
- Optimum wear protection in the high load range
- Extremely good load bearing capacity
- Especially aging and temperatures-resistant
- Structurally stable
- Resistant to cold and hot water, limited resistance to alkalis and acids
- Excellent corrosion protection
- Pumpable in central lubrication systems
- Temperature application range: - 20°C/- 4°F to 160°C/320°F. In case of life lubricated bearings the temperature of 150°C/302°F under normal conditions should not be exceeded. Short-term operation at higher temperatures is possible - please consult out Technical Service.

### Castrol Industrial Americas

150 W. Warrenville Road  
Naperville, IL 60563  
Tel (877) 641 1600  
Fax (877) 986 6447



## Product Data

### Notes for Use

- Please follow the bearing manufacturer's specifications.
- Do not mix **Castrol Optitemp® HT 2 & HT 2 EP** with other lubricating greases. In case of doubt please consult the Technical Service.
- Thoroughly clean bearings before introducing the initial fill.
- Fill bearing housing only about half-full with **Castrol Optitemp® HT 2 & HT 2 EP**

### Typical Properties

	Unit	Value		Test Method
<b>Optitemp® HT 2</b>	-	2	2 EP	-
Article no.	-	08316	VP458	-
Color	-	Dark Yellow	Black	Visual
Base	-	Inorganic thickener	Inorganic thickener + MoS <sub>2</sub>	-
Consistency / NLGI grade	-	2		DIN 51818
Worked penetration Pw 60	0.1mm	265-295		DIN ISO 2137
Difference: Pw 100,000 – Pw 60	0.1mm	50		-
Dropping point	°C °F	None		DIN ISO 2176
Water resistance @ 90°C/194°F	-	0 (no change)		DIN 51807 T. 1
Corrosion protection (SKF Emscor)	-	0/0		DIN 51802
Oxidation resistance at 100h/ 100°C/212°F, pressure drop	Bar	0.4		DIN 51808
Four ball o.k load	N	1800	2600	DIN 51350

These technical data are based on average test results. Minor deviations may occur from case to case. Above data are based on extensive tests and practical experience. Considering the wide range of application requirements, they cannot, however, guarantee success in every single case. We therefore recommend practical trials. We reserve the right to change the product composition with a view to further improvement.

All reasonable care has been taken to ensure that this information is accurate as of the date of printing. Nevertheless, such information may be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

**Castrol Industrial Americas**  
 150 W. Warrenville Road  
 Naperville, IL 60563  
 Tel (877) 641 1600  
 Fax (877) 986 6447